



A HISTORY OF BEING AHEAD OF OUR TIME

## PRODUCT DESCRIPTION: HOG HEAVEN

### GENERAL SPECIFICATIONS:

**SURFACE:**

<b>Type:</b>	100% Nitrile Rubber (15% Recycled Content)
<b>Thickness:</b>	.120"
<b>Durometer:</b>	65
<b>Tensil:</b>	1100

**CUSHION:**

<b>Type:</b>	Nitrile/PVC
<b>Thickness:</b>	.5" or .75"
<b>Density:</b>	5 lbs / ft <sup>3</sup>

**OVERALL THICKNESS:** .628" or .875"

### FEATURES:

- U.V. Stable
- Solid Nitrile Rubber top surface for excellent chemical resistance.
- Textured Nitrile Rubber surface for superior slip resistance.
- ASTM C1028-96 Static Coefficient of Friction: Dry = .92 Wet = .86
- Closed-cell Nitrile/PVC cushion backing provides long lasting comfort
- Nitrile Rubber border remains flexible for the life of the mat and will not crack or curl.
- Available in 24", 33", and 46" widths up to 22' in length.
- Available in black and OSHA approved striped borders. Colors: Yellow, Red, Green, & Orange
- Cushion is permanently bonded to the Nitrile Rubber top and will not delaminate like mats with glued on cushion.
- Passes Flammability Standard DOC-FF-1-70
- Passes ATTCC Test Method 134-1996 Electrostatic Propensity of Carpets: Maximum Voltage Negative 0.7 KV
- Static Decay Test Method 4046 Federal Standard 101B/NFPA 99 12-4.1.3.8 (f)(3)(i) - Maximum Time Recorded: .91 sec.
- Anti-Static: ANSI/ESD 57-1 1994 Protection of Electrostatic Discharge of Suseceptible Items: Flooring Materials
 

Surface to Ground -	2.1 x 10 <sup>7</sup> ohms @ 50% Relative Humidity
	3.2 x 10 <sup>7</sup> ohms @ 12% Relative Humidity
Surface to Surface -	8.2 x 10 <sup>5</sup> ohms @ 50% Relative Humidity
	8.5 x 10 <sup>5</sup> ohms @ 12% Relative Humidity